

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application.

Listing of the claims:

1.-11. (CANCELED)

12. (CURRENTLY AMENDED) A method of sealing or cutting optically with at least one laser beam flexible polymeric films, the method comprising:

superposing and bringing into contact at least two of said films together by actuating a support mechanism interconnecting two jaws of an optical clamp to allow a closing of the clamp whereupon said films are pressed between said jaws about an area to be sealed/cut with the area being free of contact with at least one of said jaws,

exposing said area of the films to said at least one laser beam by directing the laser beam through an aperture of at least one of said jaws of said optical clamp, the area corresponding to a volume of said polymeric films to be sealed or cut,

providing an incident laser beam intensity, for the purpose of one of sealing and cutting said films,

increasing an intensity of the laser beam in the volume by re-injecting partly or totally an unabsorbed portion of the incident laser beam intensity that has not been absorbed by the films back to the films by using at least one reflective device, therefore improving the efficiency of the sealing or cutting method by having more light intensity of said incident laser intensity absorbed by the films.

13. (CANCELED)

14. (ORIGINAL) The method as claimed in claim 12, wherein said unabsorbed laser intensity is at least 80 % of said incident laser intensity.

15. (ORIGINAL) The method as claimed in claim 12, wherein said unabsorbed laser intensity is at least 85 % of said incident laser intensity.

16. (ORIGINAL) The method as claimed in claim 12, wherein said unabsorbed laser intensity is at least 90 % of said incident laser intensity.

17. **(ORIGINAL)** The method as claimed in claim 12, wherein said exposing an area of the films comprises:

focusing on the films the laser beam into a small spot,
scanning the small spot along the whole width of the films to obtain an elongated seal, and
controlling the scanning to obtain a high quality seal.

18. **(ORIGINAL)** The method as claimed in claim 17, wherein said scanning is continuous.

19. **(ORIGINAL)** The method as claimed in claim 17, wherein said scanning is performed by using an optical set-up that comprises at least one mirror to scan the laser beam spot on the films.

20. **(PREVIOUSLY PRESENTED)** The method as claimed in claim 12, wherein exposing of the films comprises shaping the laser beam into a line wherein said line is wide enough to cover the whole width of the films to be sealed.

21. **(PREVIOUSLY PRESENTED)** The method as claimed in claim 12, wherein said re-injecting of unabsorbed laser intensity back to the films comprises reflecting said unabsorbed laser intensity off a reflective surface on one of said jaws.

22. **(CURRENTLY AMENDED)** The method as claimed in claim 12, wherein said reflective surface is profiled to reflect back toward the films the unabsorbed laser intensity in said volume with an intensity distribution essentially the same as the incident laser intensity.

23. **(PREVIOUSLY PRESENTED)** The method as claimed in claim 22, wherein the surface of the jaws that are exposed to the unabsorbed laser intensity by the films are profiled to allow for a plurality of back and forth reflections from one jaw to the other, allowing therefore for a multi-pass of laser beam into the films.

24. **(ORIGINAL)** The method as claimed in claim 22, wherein the surface of the jaws that are exposed to the unabsorbed laser intensity by the films are profiled to allow for

three back and forth reflections from one jaw to the other, allowing therefore for four passes of laser beam into the films.

25. **(PREVIOUSLY PRESENTED)** The method as claimed in claim 21 further comprising monitoring said one of sealing and cutting by inspecting, using an optical detection assembly, said area of the films through the aperture of the clamp, while the said one of sealing and cutting is being performed.

26. **(CURRENTLY AMENDED)** A method of optically sealing and cutting flexible polymeric films with ~~at least one~~ a single laser beam having a shaped intensity profile, the method comprising:

~~shaping the intensity profile of the at least one~~ single laser beam with respect to a volume of the films to be exposed by using an optical device, the intensity profile of the single laser beam comprising a first intensity for a cut region in the volume, and a second intensity for each one of two sealed regions in the volume, to provide the desired intensity profile to provide two seal regions separated by a cut region,

superposing and bringing into contact at least two of said films together by actuating a support mechanism interconnecting two jaws of an optical clamp to allow a closing of the clamp whereupon said films are pressed between said jaws, and

exposing an area of the films ~~using appropriate optical elements, the area being referred to as a seal-cut-seal volume, to said desired intensity profile of the at least one~~ single laser beam, for the purpose of obtaining, in one exposure step, two sealed regions separated by a cut region as defined by the shaping of the intensity profile, the two sealed regions each defining a portion of the seal-cut-seal volume where the films are sealed together, and the cut region defining another portion of the seal-cut-seal volume where the films ~~have been~~ are cut, and wherein by the time the cut region is performed, the sealed regions are sealed.

27. **(PREVIOUSLY PRESENTED)** The method as claimed in claim 26, wherein the laser beam intensity profile is a Gaussian profile with a width.

28. **(PREVIOUSLY PRESENTED)** The method as claimed in claim 26, wherein each of said sealed regions are being larger than said cut region.

29. **(PREVIOUSLY PRESENTED)** The method as claimed in claim 26, wherein said beam shaping comprises the use of lenses.

30. **(CURRENTLY AMENDED)** The method as claimed in claim 26, wherein said laser beam intensity profile comprises an intensity profile having a dimension at least larger than ~~the~~ a width of said films for the purpose of covering the whole width of the films to be sealed or cut.

31. **(ORIGINAL)** The method as claimed in claim 26, wherein said shaping the laser beam intensity profile comprises focusing into a small spot the laser beam for the purpose of scanning said spot along the seal-cut-seal volume of the films.

32. **(ORIGINAL)** The method as claimed in claim 26 further comprising monitoring said sealing and cutting by inspecting said sealed regions using an optical detection assembly.

33. **(ORIGINAL)** The method as claimed in claim 32, wherein said optical detection assembly shares some of said optical elements.

34. **(CURRENTLY AMENDED)** A method of forming, sealing and cutting optically, and filling a pouch with a liquid at high speed, said method comprising the steps of:

i) providing a vertical tube, made of polymeric film, that is at least partially filled with a liquid;

ii) flattening a filled section of said tube by actuating a support mechanism interconnecting two jaws of an optical clamp to allow a closing of the clamp whereupon said films are pressed between said jaws about a section of the films to be sealed/cut, with the section being free of contact with at least one of said jaws, and for a determined time interval for subsequent optical sealing and cutting of said section of said tube;

iii) exposing said section of said tube to an intensity profile of at least one laser beam, for a time exposure interval τ , to heat in a controlled manner said section of said tube, said intensity profile being shaped to provide a corresponding absorbed intensity profile in said section of said tube;

iv) providing a desired heat amount to said section of said tube by optimizing a combination of said absorbed intensity profile, said time exposure interval τ , and by heating if required said optical sealing clamp;

v) obtaining as a result two seals across said section of said tube, and simultaneously severed region between the seals to form a top seal for a filled pouch that is separated from said tube and a bottom seal for said vertical tube.

35. **(ORIGINAL)** The method as claimed in claim 34, wherein said providing a vertical tube comprises the steps of:

providing, in roll form, a polymeric film,

drawing said film by drawings means, over a tube former to form said vertical tube having an overlapped vertical film edge,

sealing said overlapped vertical edge with a vertical sealer to form a vertical seal,

continuously feeding a liquid within said tube below said vertical sealer and above said optical sealing clamp.

36. **(PREVIOUSLY PRESENTED)** The method as claimed in claim 34, wherein said optical sealing clamp comprises:

two jaws wherein at least one of said jaws can be moved to allow a closing and an opening of the clamp;

one of said jaws, being a contact jaw, to bring into contact an inner wall of said section of said tube;

the other jaw, being an optical jaw, having an aperture to let said at least one laser beam intensity pass through it, providing the exposing of the section of the tube to the laser beam, and wherein said aperture is wide enough to allow to optically seal or cut the whole width of said section of said tube; and

support means to interconnect said jaws and to allow a controlled opening and closing of the clamp.

37. **(CANCELED)**

38. **(PREVIOUSLY PRESENTED)** The method as claimed in claim 36, wherein said aperture comprises an optical window made of a material transparent to the laser beam.

39. **(ORIGINAL)** The method as claimed in claim 36, wherein said contact jaw has a profile to compress said inner wall of said tube together either by applying pressure or tension on said tube at the point of sealing and cutting.

40. **(ORIGINAL)** The method as claimed in claim 39, wherein said support means comprises an interconnection on at least one end of said jaws that leaves a free space between the jaws to let the tube pass through and wherein said support means provides for said opening to be large enough to allow for said filled pouch to pass through.

41. **(PREVIOUSLY PRESENTED)** The method as claimed in claim 36, further comprising re-injecting, at least partially, said laser beam intensity that has not been absorbed in step iii) by means of a reflective property of said optical sealing clamp, to enhance in a controlled manner said desired heat in the said section of said tube.

42. **(ORIGINAL)** The method as claimed in claim 41, wherein said contact jaw has a profiled surface that reflects partly or totally the laser beam intensity that has not been absorbed in step iii) back to the tube.

43. **(ORIGINAL)** The method as claimed in claim 42, wherein said optical jaw has a profiled surface that reflects partly or totally the laser beam intensity that has not been absorbed by the tube back to the tube.

44. **(PREVIOUSLY PRESENTED)** The method as claimed in claim 43, wherein the surface of the jaws are profiled to allow for a plurality of back and forth reflections from one jaw to the other, allowing therefore for a multi-pass of the laser beam intensity into the films.

45. **(ORIGINAL)** The method as claimed in claim 43, wherein the surface of the jaws are profiled to allow for three back and forth reflections from one jaw to the other, allowing therefore for four passes of the laser beam intensity into the films.

46. **(ORIGINAL)** The method as claimed in claim 34, wherein said exposing comprises:
focusing on said section of said tube the laser beam intensity into a small spot;
scanning the small spot along the whole width of said section of said tube to obtain an elongated seal; and

controlling the scanning to obtain a high quality seal.

47. **(ORIGINAL)** The method as claimed in claim 46, wherein said scanning is continuous in time.

48. **(ORIGINAL)** The method as claimed in claim 46, wherein said scanning is performed by using an optical set-up that comprises at least one mirror to scan the laser beam spot on the films.

49. **(ORIGINAL)** The method as claimed in claim 34, wherein said exposing said section of said tube comprises shaping the laser beam into a line wherein said line is wide enough to cover the whole width of the section of the tube to be sealed.

50. **(PREVIOUSLY PRESENTED)** The method as claimed in claim 34, wherein the desired intensity profile is a Gaussian profile with a width.

51. **(ORIGINAL)** The method as claimed in claim 34, wherein said beam intensity being shaped is performed by using a lenses and optical filters assembly.

52. **(ORIGINAL)** The method as claimed in claim 34, wherein said desired intensity profile comprises an intensity profile having a dimension at least larger than the width of said tube for the purpose of covering the whole width of the tube to be sealed and cut.

53. **(ORIGINAL)** The method as claimed in claim 36 further comprising monitoring said sealing and cutting while said seals are being performed by inspecting, using an optical detection assembly, said section of said tube through the optical window of the optical sealing clamp.

54. **(CURRENTLY AMENDED)** A method of sealing or sealing-and-cutting packages made with polymeric films using at least one laser source and at least one optical sealing clamp, the method comprising the steps of:

- i) providing a partially or completely formed package that is partially or completely filled with its content or being filled with its content;

- ii) superposing and bringing into contact an inner wall of a section of said package for subsequent sealing by actuating two jaws of an optical sealing clamp to

allow a closing of the clamp whereupon said films are pressed between said jaws about said section of said films to be sealed/cut, the section being free of contact with at least one of said jaws;

iii) exposing for a time exposure interval τ , said section of said package to an intensity profile of at least one laser beam by directing the laser beam through an aperture of at least one of said jaws of the clamp to heat in a controlled manner said section of said package, said intensity profile being shaped to provide a corresponding absorbed intensity profile in said section of said package;

iv) providing a desired heat amount to said section of said package in order to perform one of a sealing operation and a sealing-and-cutting operation, by optimizing a combination of said absorbed intensity profile, said time exposure interval, and by heating said optical sealing clamp upon demand;

v) obtaining as a result in the case of the sealing operation, a seal across said section of said package, and in the case of the sealing-and-cutting operation, two sealed regions across said section of said package and simultaneously a cut region between the two sealed regions where the package is cut.

55. **(ORIGINAL)** The method as claimed in claim 54, wherein step i) comprises:

providing, in roll form, two polymeric film sheets,

drawing one of said film sheets over a packaging station where the content of the package is deposited on the film,

drawing the second film sheet over said content to form said partially formed package.

56. **(ORIGINAL)** The method as claimed in claim 54, wherein step i) comprises providing a tube made of polymeric film.

57. **(ORIGINAL)** The method as claimed in claim 54, wherein step i) comprises providing a bag made of a polymeric film.

58. **(PREVIOUSLY PRESENTED)** The method as claimed in claim 54, wherein one of said two jaws is a movable jaw to allow a closing and an opening of the clamp;

one of said jaws, being a contact jaw, to bring into contact said inner wall of said section of said package;

the other jaw, being an optical jaw, having an aperture to let said at least one laser beam intensity pass through it, providing the exposing of the section of the package to the laser beam, and wherein said aperture is wide enough to allow said one of an optically sealing and optically cutting of the whole width of said section of said package; and

support means to interconnect said jaws and to allow a controlled opening and closing of the clamp.

59. **(CANCELED)**

60. **(PREVIOUSLY PRESENTED)** The method as claimed in claim 58, wherein said aperture comprises an optical window made of a material transparent to the laser beam.

61. **(ORIGINAL)** The method as claimed in claim 58, wherein said contact jaw has a profile to compress said inner wall of said package together either by applying pressure or tension on said package at the point of sealing and cutting.

62. **(ORIGINAL)** The method as claimed in claim 61, wherein said support means comprises an interconnection on at least one end of said jaws that leaves a free space between the jaws to let the package pass through and wherein said support means provides for said opening to be large enough to allow for said filled package to pass through.

63. **(ORIGINAL)** The method as claimed in claim 58, further comprising re-injecting, partially or totally, said laser beam intensity that has not been absorbed in step iii) by means of a reflective property of said optical sealing clamp, to enhance in a controlled manner heat in the said section of said package.

64. **(PREVIOUSLY PRESENTED)** The method as claimed in claim 63, wherein said contact jaw has a profiled surface that reflects at least partially the laser beam intensity that has not been absorbed in step iii) back to the package.

65. **(PREVIOUSLY PRESENTED)** The method as claimed in claim 64, wherein said optical jaw has a profiled surface that reflects at least partially the laser beam intensity that has not been absorbed by the package back to the package.

66. **(ORIGINAL)** The method as claimed in claim 65, wherein the surface of the jaws are profiled to allow for a plurality of back and forth reflections from one jaw to the other, allowing therefore for a multi-pass of the laser beam intensity into the films.

67. **(ORIGINAL)** The method as claimed in claim 65, wherein the surface of the jaws are profiled to allow for three back and forth reflections from one jaw to the other, allowing therefore for four passes of the laser beam intensity into the films.

68. **(ORIGINAL)** The method as claimed in claim 54, wherein said exposing comprises:
focusing on said section of said section of said package the laser beam intensity into a small spot;
scanning the small spot along the whole width of said section of said package to obtain an elongated seal; and
controlling the scanning speed to obtain a high quality seal.

69. **(ORIGINAL)** The method as claimed in claim 68, wherein said scanning is continuous in time.

70. **(ORIGINAL)** The method as claimed in claim 68, wherein said scanning is performed by using an optical set-up that comprises at least one mirror to scan the laser beam spot on the films.

71. **(ORIGINAL)** The method as claimed in claim 54, wherein said exposing said section of said package comprises shaping the laser beam into a line wherein said line is wide enough to cover the whole width of the section of the package to be sealed.

72. **(PREVIOUSLY PRESENTED)** The method as claimed in claim 54, wherein the desired intensity profile is a Gaussian profile with a width.

73. **(ORIGINAL)** The method as claimed in claim 54, wherein said beam intensity being shaped is performed by using a lenses and optical filters assembly.

74. **(ORIGINAL)** The method as claimed in claim 54, wherein said desired intensity profile comprises an intensity profile having a dimension at least larger than the width of

said package for the purpose of covering the whole width of the package to be sealed and cut.

75. **(PREVIOUSLY PRESENTED)** The method as claimed in claim 58 further comprising monitoring said one of a sealing and a sealing-and-cutting operation by inspecting, using an optical detection assembly, said section of said package through the aperture of the optical sealing clamp, while said one of a sealing and a sealing-and-cutting operation is being performed.

76.-79. **(CANCELED)**

80. **(CURRENTLY AMENDED)** A method of sealing or cutting optically with at least one laser beam polymeric sheets, the method comprising:

superposing and bringing into contact at least two of said sheets together by actuating a support mechanism interconnecting two jaws of an optical clamp to allow a closing of the clamp whereupon said films are pressed between said jaws about an area of said sheets,

exposing ~~an~~ the area of the sheets, ~~the area corresponding to a sealing volume,~~ to the at least one laser beam by directing the laser beam on the area, through an aperture of at least one of said jaws of the clamp, the area corresponding to at least a portion of a volume of said sheets to be sealed or cut

providing an incident laser beam intensity, for the purpose of one of sealing and cutting said sheets,

increasing an intensity of the laser beam in the ~~sealing volume~~ by re-injecting partly or totally an unabsorbed portion of the incident laser beam intensity that has not been absorbed by the sheets back to the sheets by using at least one reflective device, the at least one reflective device dividing the unabsorbed portion of the incident laser beam intensity in at least two reflected laser beams each for increasing the intensity in a different portion of the volume, thereby ~~therefore~~ improving the efficiency of the sealing or cutting method by having more light intensity of said incident laser intensity absorbed by the sheets.

81. **(CURRENTLY AMENDED)** A method of optically sealing and cutting polymeric sheets with ~~at least one~~a single laser beam having a shaped intensity profile, the method comprising:

~~shaping the intensity profile of the at least one~~single laser beam with respect to a volume of the films to be exposed ~~intensity profile by using an optical device, the intensity profile of the single laser beam comprising a first intensity for a cut region in the volume, and a second intensity for each one of two sealed regions in the volume, to provide the desired intensity profile to provide two seal regions separated by a cut region,~~

superposing and bringing into contact at least two of said sheets together by actuating a support mechanism interconnecting two jaws of an optical clamp to allow a closing of the clamp whereupon said films are pressed between said jaws, and

exposing an area of the sheets to said single laser beam, the area being referred to as a seal-cut-seal volume, ~~to said desired intensity profile of the at least one single laser beam by directing said desired intensity through an aperture of the clamp for the purpose of obtaining, in one exposure step, two sealed regions separated by a cut region as defined by the shaping of the intensity profile, the two sealed regions each defining a portion of the seal-cut-seal volume where the sheets are sealed together and the cut region defining another portion of the seal-cut-seal volume where the sheets have been~~are cut, and wherein by the time the cut region is performed, the sealed regions are sealed.

82. **(CURRENTLY AMENDED)** A method of sealing or sealing-and-cutting packages made with polymeric sheets using at least one laser source and at least one optical sealing clamp, the method comprising the steps of:

i) providing a partially or completely formed package that is partially or completely filled with its content or being filled with its content,

ii) superposing and bringing into contact an inner wall of a section of said package for subsequent sealing by actuating two jaws of an optical sealing clamp to allow a closing of the clamp whereupon said films are pressed between said jaws about the section to be sealed/cut, the section being free of contact with at least one of said jaws,

iii) exposing for a time exposure interval τ , said section of said package to an intensity profile of at least one laser beam by directing the laser beam through an aperture of at least one of said jaws of the clamp, to heat in a controlled manner said section of said package, said intensity profile being shaped to provide a corresponding absorbed intensity profile in said section of said package,

iv) providing a desired heat amount to said section of said package in order to perform one of a sealing operation and a sealing-and-cutting operation, by optimizing a combination of said absorbed intensity profile, said time exposure interval, and by heating if required said optical sealing clamp,

v) obtaining as a result in the case of the sealing operation, a seal across said section of said package, and in the case of the sealing-and-cutting operation, two sealed regions across said section of said package and simultaneously a cut region between the two sealed regions where the package is cut.